



## TECHNICAL DATA SHEET

### Product code & description:

**UDC2002 WESTACURE DUCT GLOSS COATING**

### Application:

UDC2002 WESTACURE DUCT GLOSS COATING is a UV curable coating designed for offset duct application. Product has good gloss and good surface slip.

### Key Properties:

- Good gloss
- Good Flow & Levelling
- Good surface Slip
- Good abrasion resistance
- Water resistance

### Substrate:

Recommended for use on coated paper, board and Metpet. When overprinting on highly absorbent substrates it is always advised to check their performance on the actual batch of stocks used before commencing a full production run.

Suitable for use on coated Metalized Polyester ( $\geq 42$  dynes/cm) - preferably primer coated by water-based varnish.

### Instructions for Use

- |                        |                                    |
|------------------------|------------------------------------|
| • Stir well before use |                                    |
| • Application          | Offset                             |
| • Viscosity            | Ready for use                      |
| • Varnish coat weight  | 1.5 — 2.5 gsm (as per requirement) |
| • Cleaning             | Immediately with proper solvent    |

### Curing:

The OP coating converts into a solid film by radical polymerization initiated by UV radiation in the range of 200 -400 nm. Capacity of the lamp is 80 -120 watts/cm.

### Machine Speed

Depends on the Type and age of the lamp

## Technical Characteristics:

Color Appearance:	Clear viscous liquid
Viscosity by Rotothinner@30°C:	20 ± 2 Poise
Specific gravity:	1 – 1.2
Volatility:	0 %

## Product safety:

UV products are generally considered to be non-toxicological. However, during handling and use, avoid inhalation of vapor and direct eyes or skin contact. It can be irritating, wash and rinse immediately with soap & water. Protective eyewear and latex gloves are recommended while using this product. Refer MSDS for additional handling and safety information.

## Shelf life:

UDC2002 is stable for 6 months when stored in its original container at temperatures between 5°C and 25°C, away from direct sunlight. Contaminated material should not be returned to the original container or re-used.

## Cleaning:

Clean the plates, rubber roller, steel roller, anilox roll and other equipment with recommended cleaning agent, after use.

## Packaging:

This product is available in 20Kg plastic pail.

**NOT SUITABLE FOR DIRECT CONTACT FOOD PACKAGING**

## Disclaimer:

**This information is furnished without warranty, expressed, or implied, except that it is accurate to the best knowledge of Westtek Enterprises Private Limited. The data on the sheet is related to specific product designated herein. Westtek Enterprises Private Limited assumes no legal responsibility for use or reliance upon these data.**

Issued Date: Feb 2023- Version: V1.1

---